

SECTION 079200 - JOINT SEALANTS

PART 1 GENERAL

1.1 SECTION INCLUDES

- A. Nonsag gunnable joint sealants.
- B. Self-leveling pourable joint sealants.
- C. Joint backings and accessories.

1.2 RELATED REQUIREMENTS

- A. Section 093000 - Tiling: Sealant between tile and plumbing fixtures and at junctions with other materials and changes in plane.

1.3 REFERENCE STANDARDS

- A. ASTM C794 - Standard Test Method for Adhesion-in-Peel of Elastomeric Joint Sealants.
- B. ASTM C834 - Standard Specification for Latex Sealants.
- C. ASTM C920 - Standard Specification for Elastomeric Joint Sealants.
- D. ASTM C1087 - Standard Test Method for Determining Compatibility of Liquid-Applied Sealants with Accessories Used in Structural Glazing Systems.
- E. ASTM C1193 - Standard Guide for Use of Joint Sealants.
- F. ASTM C1248 - Standard Test Method for Staining of Porous Substrate by Joint Sealants.
- G. ASTM C1330 - Standard Specification for Cylindrical Sealant Backing for Use with Cold Liquid-Applied Sealants.

1.4 SUBMITTALS

- A. See Section 013000 - Administrative Requirements for submittal procedures.
- B. Product Data: Submit manufacturer's technical datasheets for each product to be used; include the following:
 - 1. Physical characteristics, including movement capability, VOC content, hardness, cure time, and color availability.
 - 2. List of backing materials approved for use with the specific product.
 - 3. Substrates that product is known to satisfactorily adhere to and with which it is compatible.
 - 4. Substrates the product should not be used on.
- C. Color Cards for Selection: Where sealant color is not specified, submit manufacturer's color cards showing standard colors available for selection.

- D. Preconstruction Laboratory Test Reports: Submit at least four weeks prior to start of installation.

1.5 QUALITY ASSURANCE

- A. Preconstruction Laboratory Testing: Arrange for sealant manufacturer(s) to test each combination of sealant, substrate, backing, and accessories.
 - 1. Adhesion Testing: In accordance with ASTM C794.
 - 2. Compatibility Testing: In accordance with ASTM C1087.
 - 3. Allow sufficient time for testing to avoid delaying the work.
 - 4. Deliver sufficient samples to manufacturer for testing.
 - 5. Report manufacturer's recommended corrective measures, if any, including primers or techniques not indicated in product data submittals.

PART 2 PRODUCTS

2.1 MANUFACTURERS

- A. Nonsag Sealants:
 - 1. Dow: www.dow.com.
 - 2. Sika Corporation: usa.sika.com.
 - 3. Tremco Commercial Sealants & Waterproofing: www.tremcosealants.com.
 - 4. Substitutions: See Section 016000 - Product Requirements.

2.2 JOINT SEALANT APPLICATIONS

- A. Scope:
 - 1. Exterior Joints:
 - a. Seal the following joints:
 - 1) Joints between doors, windows, and other frames or adjacent construction.
 - 2) Joints between different exposed materials.
 - 2. Interior Joints:
 - a. Do not seal interior joints indicated on drawings as not sealed.
 - b. Do not seal gaps and openings in gypsum board and suspended ceilings
 - c. Do not seal through-penetrations in sound-rated assemblies that are also fire-rated assemblies.
 - d. Seal the following joints:
 - 1) Joints between door frames and window frames and adjacent construction.
 - 3. Do Not Seal:
 - a. Joints where sealant is specified to be furnished and installed by manufacturer of product to be sealed.
 - b. Joints where sealant installation is specified in other sections.
 - c. Joints between suspended ceilings and walls.
- B. Interior Joints: Use non-sag polyurethane sealant, unless otherwise indicated.
 - 1. Wall and Ceiling Joints in Nonwet Areas: Acrylic emulsion latex sealant.
 - 2. Wall and Ceiling Joints in Wet Areas: Nonsag polyurethane sealant for continuous liquid immersion.

3. Floor Joints in Wet Areas: Nonsag polyurethane non-traffic-grade sealant suitable for continuous liquid immersion.
 4. Joints between Tile in Wet Areas and Floors, Walls, and Ceilings: Mildew-resistant silicone sealant; white.
- C. Interior Wet Areas: restrooms and break rooms; fixtures in wet areas include plumbing fixtures, countertops, cabinets, and other similar items.

2.3 JOINT SEALANTS - GENERAL

- A. Colors: As indicated on drawings.

2.4 NONSAG JOINT SEALANTS

- A. Non-Staining Silicone Sealant: ASTM C920, Grade NS, Uses M and A; not expected to withstand continuous water immersion or traffic.
1. Movement Capability: Plus 100 percent and minus 50 percent, minimum.
 2. Nonstaining to Porous Stone: Nonstaining to light-colored natural stone when tested in accordance with ASTM C1248.
 3. Dirt Pick-Up: Reduced dirt pick-up compared to other silicone sealants.
 4. Color: To be selected by Architect from manufacturer's standard range.
 5. Products:
 - a. Dow; DOWSIL 790 Silicone Building Sealant: www.dow.com/#sle.
 - b. Pecora Corporation; Pecora 890 NST (Non-Staining Technology): www.pecora.com/#sle.
 - c. Tremco Commercial Sealants & Waterproofing; Spectrem 1: www.tremcosealants.com/#sle.
 - d. Substitutions: See Section 016000 - Product Requirements.
- B. Mildew-Resistant Silicone Sealant: ASTM C920, Grade NS, Uses M and A; single component, mildew resistant; not expected to withstand continuous water immersion or traffic.
1. Color: White.
 2. Products:
 - a. Dow Chemical Company; DOWSIL 786 Silicone Building Sealant: consumer.dow.com/en-us/industry/ind-building-construction.html.
 - b. Pecora Corporation; Pecora 898 NST (Non-Staining Technology): www.pecora.com/#sle.
 - c. Tremco Commercial Sealants & Waterproofing; Tremsil 200; www.tremcosealants.com
 - d. Substitutions: See Section 016000 - Product Requirements.
- C. Polyurethane Sealant: ASTM C920, Grade NS, Uses M and A; single or multi-component; not expected to withstand continuous water immersion or traffic.
1. Movement Capability: Plus 100 percent, minus 50 percent, minimum.
 2. Color: To be selected by Architect from manufacturer's standard range.
 3. Service Temperature Range: Minus 40 to 180 degrees F.
 4. Products:
 - a. Pecora Corporation; DynaFlex: www.pecora.com.
 - b. Sherwin-Williams Company; Stampede 2NS Polyurethane Sealant: www.sherwin-williams.com.

- c. Tremco Commercial Sealants & Waterproofing; Dymonic 100:
www.tremcosealants.com/#sle.
 - d. Substitutions: See Section 016000 - Product Requirements.
- D. Acrylic Emulsion Latex: Water-based; ASTM C834, single component, nonstaining, nonbleeding, nonsagging; not intended for exterior use.
- 1. Color: To be selected by Architect from manufacturer's standard range.
 - 2. Products:
 - a. Pecora Corporation; AC-20 +Silicone: www.pecora.com/#sle.
 - b. Sherwin-Williams Company; White Lightning 3006 Siliconized Acrylic Latex Caulk: www.sherwin-williams.com/#sle.
 - c. Tremco Commercial Sealants & Waterproofing; Tremflex 834:
www.tremcosealants.com/#sle.

2.5 SELF-LEVELING JOINT SEALANTS

- A. Self-Leveling Silicone Sealant: ASTM C920, Grade P, Uses M and A; single or multicomponent, explicitly approved by manufacturer for traffic exposure when recessed below traffic surface; not expected to withstand continuous water immersion.
- 1. Movement Capability: Plus 100 percent, minus 50 percent, minimum.
 - 2. Products:

2.6 ACCESSORIES

- A. Sealant Backing Rod, Closed-Cell Type:
- 1. Cylindrical flexible sealant backings complying with ASTM C1330 Type C.
 - 2. Size: 25 to 50 percent larger in diameter than joint width.

PART 3 EXECUTION

3.1 INSTALLATION

- A. Install this work in accordance with sealant manufacturer's requirements for preparation of surfaces and material installation instructions.
- B. Provide joint sealant installations complying with ASTM C1193.
- C. Install bond breaker backing tape where backer rod cannot be used.
- D. Install sealant free of air pockets, foreign embedded matter, ridges, and sags, and without getting sealant on adjacent surfaces.
- E. Do not install sealant when ambient temperature is outside manufacturer's recommended temperature range, or will be outside that range during the entire curing period, unless manufacturer's approval is obtained and instructions are followed.
- F. Nonsag Sealants: Tool surface concave, unless otherwise indicated; remove masking tape immediately after tooling sealant surface.

END OF SECTION 079200